

Stork Twin City Testing Corporation

JOB NUMBER:

30160 09-03859R

PAGE:

1 of 3

DATE:

April 6, 2009

662 Cromwell Avenue Saint Paul, MN 55114

USA

Telephone Toll Free Telefax

Website

:(651) 645-3601 :(888) 645-TEST :(651) 659-7348

:www.storktct.com

Investigative Chemistry Non Destructive Testing Metallurgical Analysis

Geotechnical Failure Analysis Materials Testing Construction Materials **Product Evaluation** Welder Qualification

EFFECTIVE THERMAL RESISTANCE OF **EPS PANELS**

Prepared for: InSoFast, LLC Attn: Mr. Ed Scherrer 7255 Commerce Circle E. Minneapolis, MN 55432

Prepared By:

Briana Hinrichs Testing Technician

Product Evaluation Department

Reviewed By:

William Stegeman

Advanced Materials Dept. Mgr.

William Stegeman

Phone: 651-659-7230

The test results contained in this report pertain only to the samples submitted for testing and not necessarily to all similar products.

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony under Federal Statues including Federal Law Title 18, Chapter 47



Stork Twin City Testing Corporation

JOB NUMBER:

30160 09-03859R

PAGE:

2 of 3

DATE:

April 6, 2009

EFFECTIVE THERMAL RESISTANCE TESTING OF EPS

INTRODUCTION:

This report presents the results of Effective Thermal Resistance Tests conducted on samples of InSoFast EPS Panel. The testing was authorized by Mr. Ed Scherrer of InSoFast, LLC on March 24, 2009. The testing and data analysis were completed on March 25, 2009.

The scope of our work was limited to conducting effective thermal resistance tests on the samples submitted and reporting the results.

SUMMARY OF RESULTS:

Sample	Effective R Value	Density, lbf/ft3	
EPS	4.45	1.39	

SAMPLE IDENTIFICATION:

The sample was identified as a 12" x 12" x 1" panel of EPS insulation.

TEST METHOD:

The specimen was allowed to condition at standard laboratory conditions of 72 ± 4°F and 50 ± 5% relative humidity for at least 40 hours prior to testing. The thermal resistance testing was conducted using ASTM Standard C518-04, "Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus" as a procedural guide. The specimen was placed in a Netzsch Heat Flow Meter; model HFM 436/3/1 ER. Steady-state heat flux measurements were made at a mean temperature of approximately 75°F using a hot face temperature of approximately 100°F and a cold face temperature of approximately 50°F. Specimen thermal resistance and thermal conductivity were determined by comparing the heat flux measurements of the specimen to measurements made on a known Standard Reference Material. Resistance values obtained from the Heat Flow Meter are best utilized for homogenous specimens.

Test Method	Test Method Title	Notes/Deviations from Method		
ASTM C518-04	Standard Test Method for Steady- State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus	The effective thermal resistance testing was conducted using ASTM Standard C518-04, as a procedural guide.		



Stork Twin City Testing Corporation

JOB NUMBER:

30160 09-03859R

PAGE:

3 of 3

DATE:

April 6, 2009

CALIBRATED TEST EQUIPMENT:

Netzsch Heat Flow Meter, model HFM 436/3/1 ER, S# 284A-1107-606000788, calibrated 12/08 Mitutoyo Caliper 12", ID MM160-008, calibrated 9/08 Mitutoyo Digimatic Indicator, ID MM160-083, calibrated 11/08 Ohaus Balance, model GT2100, calibrated 7/08

UNCALIBRATED TEST EQUIPMENT:

Neslab Chiller, model RTE-110, S# 89CML91040-7

TEST DATA:

ASTM C518 Results

SAMPLE IDENTIFICATION:	Trial #1	Trial #2	
Thickness, in	1.050	1.050	
Density lbs/ft ³	1.39	1.39	
TEST CONDITIONS:			
Temperature Gradient °F/in	51.12	51.13	
Mean Temperature, °F	75.45	75.49	
Temperature Range, °F	53.68	53.68	
Test Time, min	32.22	15.35	
RESULTS:			
Thermal Conductivity, Btu-in/(h-ft2-°F)	0.236	0.235	
Thermal Conductance, Btu/(h·ft²·°F)	0.225	0.224	
Thermal Resistivity, °F-ft²-h/Btu/in	4.23	4.25	
Thermal Resistance, °F·ft²·h/Btu	4.44	4.46	
Average Thermal Resistance, °F·ft2·h/Btu	4.45		

Density

Sample	Reading	Width, in.	Length, in.	Height, in.	Volume, ft ³	Weight, Ib	Density, pcf
EPS	1	12.045	12.041	1.046	0.09	0.12	1.39
	2	12.039	12.027	1.052			
	3	12.037	12.026	1.053			
	Average	12.04	12.03	1.05			

REMARKS:

The test materials will be retained for 14 days from the date of this report and then discarded unless we receive written notification requesting otherwise.

F:\Product\Advanced Materials\09 Completed Pjts\03859 InSoFast\03859R InSoFast Rpt Revised.doc

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony under Federal Statues including Federal Law Title 18, Chapter 47